

# TUFF

Inflatable Boat Repair  
Renew - Protect - Restore

## ECO-TUFF Application Instructions

**Surface preparation** must provide a clean dry material free from mildew, oil, wax or grease. If your boat has ever been coated with Armorall or any other poly type protectorant, boat must be cleaned with a strong cleaner to remove any residual coating. Leaks must be repaired prior to application. If mildew is present wash boat thoroughly with a solution of one part household bleach and three parts soapy water. After surface is cleaned, dried and repaired, begin application. **PLEASE NOTE: with any coating not all factors can be controlled - Test a small area as to compatibility of product before committing to do the complete boat.**

TUFF ECO-COAT APPLICATION - Surface must be clean and dry as well as free from wax, grease, oil and mildew before application. Topcoat should be applied 2 -24 hours after basecoat is applied. Do not apply outside if rain is forecast within 12 hours. Stir well, May be thinned with maximum 10% with distilled water. May be brushed rolled or sprayed, Allow 3-4 hours for first coat to dry before applying second coat. Allow a minimum of 48 hrs before using inflatable. It may take up to two to three weeks for topcoat to attain full strength. Topcoat cleans up with water.

**TUFF ECO -TOPCOAT** is an easy to apply waterborne acrylic vinyl. It will create a rugged flexible surface that seals and shields the material it covers Topcoat provides an extremely tough flexible surface. It is available in Silver Gray, White Cloud, Black, Signal Red and Orange.